



Technical Data Sheet

ACS Material Mesoporous Molecular Sieve Nano H-ZSM-5

Table of Contents

[1 – Preparation Method](#)

[2 – Characterizations](#)

[3 – Application Fields](#)

Contact Information:

Manufacturer: ACS Material, LLC.

Address: 959 E Walnut St. Suite 100

Pasadena, CA 91106, USA

Phone: (866)-227-0656

Fax: (781)-518-0284

E-Mail: contact@acsmaterial.com


Revision: 062823

1. Preparation Method


Hydrothermal synthesis method

2. Characterizations


Type	P-26	P-52	P-87	P-91	P-371
Shape:	Sphere	Sphere	Sphere	Sphere	Sphere
SiO ₂ /Al ₂ O ₃ Molar Ratio:	26	52	87	91	371
Na%:	<0.1	<0.1	<0.1	<0.1	<0.1
Crystal Size (nm):	800	800	800	800	800
H ₂ O (wt.%):	<5	<5	<5	<5	<5
BET surface area (m ² /g):	≥362	≥362	≥362	≥362	≥362
Relative Crystallization (%):	100	98	100	99	96




Typical SEM Image of ACS Material Nano H-ZSM-5 P-26




Typical SEM Image of ACS Material Nano H-ZSM-5 P-52



Typical SEM Image of ACS Material Nano H-ZSM-5 P-87



Typical SEM of ACS Material Nano H-ZSM-5 P-91



Typical SEM of ACS Material Nano H-ZSM-5 P-371

3. Application Fields

- 1) Catalyst
- 2) Adsorbent

Disclaimer: ACS Material, LLC believes that the information in this Technical Data Sheet is accurate and represents the best and most current information available to us. ACS Material makes no representations or warranties either express or implied, regarding the suitability of the material for any purpose or the accuracy of the information contained within this document. Accordingly, ACS Material will not be responsible for damages resulting from use of or reliance upon this information.